



DIVERSIFIED

TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

March 20, 2014

Ms. Christine Walsh
CULP CONTRACT FABRICS
1823 Eastchester Drive
High Point, NC 27265

Reference: Flammability Test Report
Lab Identification No. 9601
Invoice No. 40362 (Attached)

Dear Ms. Walsh:

One (1) fabric sample, identified as **LARGO**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> <u>(seconds)</u>	<u>Weight Loss</u> <u>(percent)</u>
1	0.0	3.78
2	0.0	13.27
3	0.0	14.34
4	0.0	9.85
5	0.0	9.50
6	0.0	10.74
7	0.0	13.05
8	0.0	11.19
9	0.0	11.40
10	0.0	11.90
AVG.	0.0	10.90

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment