



DIVERSIFIED
TESTING LABORATORIES, INC.
WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 5, 2019

Mr. Alex Croker
HANES INDUSTRIES, INC.
P.O. Box 457
Conover, NC 28613

Reference: Laboratory Test Report
Lab Identification No. 35311
Invoice No. 66492

Dear Mr. Croker:

One (1) fabric sample, identified as Stacked, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2019 Edition, (Test 1)". The results are as follows:

<u>Specimen Number</u>	<u>Test Results</u>	
	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	19.62
2	0.0	19.57
3	0.0	24.06
4	0.0	14.66
5	0.0	25.00
6	0.0	25.36
7	0.0	14.87
8	0.0	28.85
9	0.0	24.47
10	0.0	19.81
AVG	0.0	21.62

The sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Brian S. Dement

BSD/mr

